




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : G02F 1/15	A1	(11) International Publication Number: WO 00/28374 (43) International Publication Date: 18 May 2000 (18.05.00)
(21) International Application Number: PCT/EP99/08572 (22) International Filing Date: 9 November 1999 (09.11.99) (30) Priority Data: 198 51 717.3 10 November 1998 (10.11.98) DE (71) Applicants (for all designated States except US): MAGNA REFLEX HOLDING GMBH [DE/DE]; Industriestrasse 3, D-97959 Assamstadt (DE). AXIVA GMBH [DE/DE]; Industriepark Höchst, k 801, D-65926 Frankfurt / Main (DE). (72) Inventors; and (75) Inventors/Applicants (for US only): ATHENSTAEDT, Wolfgang [AT/AT]; Algersdorferstrasse 66c, A-8020 Graz (AT). MACHER, David [AT/AT]; Maigasse 8, A-8570 Voitsberg (AT). ZORN, Heinz [AT/AT]; Hof 285, A-8063 Eggersdorf (AT). SOCZKA-GUTH, Thomas [DE/DE]; Sophie-Reinheimer-Strasse 12, D-65719 Hofheim (DE). (74) Agent: PFENNING, MEINIG & PARTNER GBR; Mozartstrasse 17, D-80336 München (DE).		(81) Designated States: AE, AL, AU, BA, BB, BG, BR, CA, CN, CR, CU, CZ, DM, EE, GD, GE, HR, HU, ID, IL, IN, IS, JP, KP, KR, LC, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, TZ, UA, US, UZ, VN, YU, ZA, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: ELECTROCHROMIC GLASS COMPONENT (57) Abstract The invention relates to an electrochromic glass component, particularly for motor vehicle mirrors, which contains a doped ion-conducting basic polymer (4) as the ion-conducting layer. The electrochromic glass component consists, for example of a glass substrate (1) as well as a layer system having an electrochromic layer (2), a mirror layer (3), a doped polymer membrane (4), for example of polybenzimidazole polymer, a proton store (5), a rear electrode (6) and a polyester film (7). The layer system is sealed by a seal (8) which closes the coating system towards the glass substrate (1).		



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Electrochromic glass component

5

FIELD OF INVENTION

The invention relates to an electrochromic glass component, particularly for motor vehicle mirrors, which contains a doped ion-conducting basic polymer as the ion-conducting layer.

10

BACKGROUND OF INVENTION

Electrochromic mirrors, particularly for motor vehicles, are known in the state of the art. The essential element of these electrochromic mirrors is a layer of electrochromic material. A material is termed electrochromic when it changes its optical constants (n , k) and hence its optical properties on application of an electric field. Typical examples of such electrochromic materials are WO_3 and MoO_3 , which are virtually colourless when applied to a substrate in thin layers. An electrochromic layer may change its optical properties by oxidation or reduction processes. If protons move in such a layer, in the case of tungsten oxide there is a reduction to blue tungsten bronze. The intensity of colouration is determined by the quantity of charge which has flowed in the layer.

15

20

25

30

Numerous electrochromic mirrors, particularly for motor vehicles, are now known from the state of the art and have electrochromic layers of this type in different layered structures.

35

German 3 008 768 describes an electrochromic mirror which essentially consists of a layer system built on

a glass substrate at least one electrochromic layer, at least two electrodes, at least one proton-conducting layer and at least one proton-delivering and one proton-storing layer being present.

5 The optical change properties of a mirror of this type are determined, inter alia, by the proton conductivity of the proton-conducting layer. The higher the proton conductivity, the higher also the rate of
10 change of reflection. In the mirrors of the state of the art, proton-conducting glass plates, which were soaked with sulphuric acid, have been used hitherto as proton-conducting layers (for example in German Offenlegungsschrift 2 504 905) or as in German 3 008
15 768 so-called solid ion-conducting layers.

It has been shown all these ion-conducting layers from the state of the art used hitherto for the electrochromic glass components still do not have
20 satisfactory results with regard to ion conductivity. Furthermore, it is disadvantageous for the mirrors of the state of the art, that the ion-conducting layers described there are either too thick or are too complex and expensive as regards their mode of manufacture.
25

SUMMARY OF INVENTION

The object of the present invention is therefore,
30 starting from the electrochromic mirror as described in German 3 008 768, to indicate a significantly improved embodiment which is characterised particularly by an ion-conducting layer which is favourable to apply as regard to manufacture and processing and
35 furthermore has a high ion conductivity, with which

it is possible to change the electrochromic layer quickly.

5 The invention is achieved by the characterising features of patent claim 1. The sub-claims show advantageous further developments.

10 According to the invention it is thus proposed to use a doped ion-conducting basic polymer as the ion-conducting layer. It has been shown that these doped ion-conduction basic polymers are particularly well suited. The doped ion-conducting basic polymer is preferably selected from polybenzimidazoles (PBI), polypyridines, polyimidazoles, polybenzthiazoles, 15 polybenzoxazoles, polyquinolines, polythiazoles, polyoxadiazoles and polytetrapyrenes. The ion-conducting layer is thus a layer which preferably conducts protons. However, in principle the layer is also suitable for other ions, such as for example 20 lithium.

DESCRIPTION OF THE DRAWINGS

25 The invention is illustrated in more detail below using Figure 1 and Figure 2.

Figure 1 shows an electrochromic glass component of the invention, here as a motor vehicle mirror.

30 Figure 2 shows the concrete structure of a mirror.

DESCRIPTION OF THE INVENTION

35 The electrochromic glass component, which is used as a motor vehicle mirror, consists of a glass substrate

1 having a thickness of 2 mm. A layer system which has the following successive layers is applied to this substrate 1.

5 An electrochromic layer 2 of tungsten oxide having a thickness of ~ 700 nm, a mirror layer 3 of palladium having a thickness of ~ 70 nm, a polymer membrane 4 of polybenzimidazols polymer having a thickness of 30 μ m, a proton store 5 of tungsten trioxide having a
10 thickness of 700 nm, a rear electrode 6 of gold having a thickness of 100 nm, a polyester film 7 having a thickness of about 175 μ m as well as a sealing layer 8 of traditional plastics, which wraps around the entire coating system including the glass substrate 1 and thus seals the coating system comprising layers 2
15 to 7. Seal 8 is only interrupted by copper wires 5, which contact the mirror layer 3 on the one side and the rear electrode 6 on the other side to apply a voltage to the latter.

20 Figures 2a and 2b show the electrochromic glass component according to Figure 1, but the function of a glass component of this type becomes visible here. In the exemplary embodiment according to Figure 2, a
25 primer 10 for better adhesion promotion is also applied between the electrochromic layer 2 and the mirror layer 3. Figure 2a thus shows the light position and Figure 2b the dark position.

30 It is particularly preferable for the electrochromic glass component of the invention if the doped ion-conducting polymer is present in the form of a polymer membrane. A proton-conduction polymer membrane
35 particulate preferred. It should be emphasised in particular for the ion-conducting layer according to

the invention that it may be applied easily using all conventional techniques. Examples of these are screen printing, immersion, spraying, blade coating or also application of a gel.

5

According to the present invention it is particularly preferable if the polymer membrane is a polybenzimidazole.

10

It should be emphasised in particular for the electrochromic glass component of the invention that the doped ion-conducting layer has particularly good properties with regard to its ion conductivity if the ion-conducting layer is doped with an acid, in particular with a strong acid. It is preferable if the pKa value of the doping acid ≤ 4.5 , preferably ≤ 3.5 for the first dissociation stage at 25 °C. For acid it has proved to be particularly advantageous if the acid is a phosphoric acid, in particular a polyphosphoric acid. Acid treatment of polybenzimidazoles is described in United States 5 599 639, to which reference is made expressly here.

15

20

25


It is particularly preferable for the electrochromic glass component of the invention if it contains a proton-conducting polymer membrane of polybenzimidazole.

30

35

Polymer membranes of this type, which are composed of polybenzimidazoles and are proton-conducting, are known from the state of the art, for example from United States 5 017 681. All named polybenzimidazoles in the above-mentioned United States patent specification may be used in principle for the proton-conducting layer of the invention. It is particularly

preferable if the polymer consists of a polybenzimidazole having a molecular weight between 1,000 and 500,000 which consists of repeating units of the following structural formula:



It has proved to be particularly favourable for the electrochromic glass component if the ion-conducting layer described in more detail above is used at a layer thickness of 1 μm to 1 mm, preferably 5 μm to 100 μm . Application of the layer, in particular the polymer membrane, may thus be effected by screen printing, immersion, spraying, blade coating or even as a gel. Provision is thus made according to the invention in that the layer is applied either as a finished film or is even produced directly on the substrate or a layer lying underneath. These application procedures may also be used in combination.

The electrochromic layer, which preferably has a layer thickness of 300 nm to 8,000 nm, preferably 300 nm to 8,000 nm, preferably consists of WO_3 , MoO_3 , IrO_2 or mixed oxides thereof. The electrochromic layer is applied by sputtering, sol-gel or by vapour deposition.

The electrodes, which are necessary for constructing the layer system of the invention, are preferably

metallic layers having a layer thickness of 50 nm to 10 μ m. Examples of layers of this type are those which contain rhodium, palladium, platinum or alloys thereof.

5

According to a preferred embodiment, provision is made in that a metallic electrode layer at the same time forms a reflector which may accept protons. This reflector preferably consists of a layer having a layer thickness of 30 nm to 500 nm, which contains rhodium, palladium, platinum or alloys thereof.

10

15

20

25

30

As already described in German 3 008 768, it is also preferable for the electrochromic glass component of the invention if the ion-delivering layer and the ion-storing layer at the same time form a layer or a composite. According to a preferred embodiment of the invention, provision is thus made in that the proton-storing layer is the electrochromic layer at the same time. In this case, for example a WO_3 layer, thus functions at the same time as a hydrogen ion-storing layer and as an electrochromic layer. According to a preferred embodiment, the composite consists of the proton-storing and at the same time proton-delivering layer on a film, preferably a polyester film with metallisation which is the counter-electrode. Instead of the film of polyester, glass, metal or other plastics are suitable as substrate materials for the composite.

35

With regard to the possible layered structure variants of the electrochromic glass component of the invention, reference is made to German 3 008 768 and the layered structure described therein.

However, it is preferable for the glass component of the invention if the glass component has been constructed from two layered composites. Hence, in the manufacture of the electrochromic glass component according to a preferred embodiment, a first layer system is constructed on a glass substrate, an electrochromic layer applied thereto and metallisation as a reflector. These layers are produced by means of sputtering processes.

The second part of the layer system is then a composite which consists of a proton-storing layer, metallisation and a film arranged thereabove, in particular a polyester film. This composite is manufactured in a separate process step and then joined to the above-mentioned first layered composite of the layer system. This procedure facilitates cost-effective and simple manufacture of the electrochromic glass component.

A further favourable embodiment of the invention makes provision, if it is necessary, in that adhesion-promoting layers for better bonding are applied between the individual layers. Examples of this are chromium, titanium or even silicon oxides SiO_x . For application as motor vehicle mirrors, provision is also made in that the layer system is tightly sealed externally. Hence the layer system may be sealed at the end-faces and a final layer, that is a layer opposite the glass substrate seen in the viewing direction, may be provided with a protective layer, for example a diffusion barrier. Diffusion barriers of this type have a water permeability $< 1,000$, preferably $< 100 \text{ cm}^3$. For motor vehicle mirrors it has proved to be particularly favourable if

the glass substrate is a reflection-reducing thin glass having a layer thickness of 0,1 to 3 mm. For motor vehicle mirrors it is also advisable if a transparent conductive layer for heating the mirror is applied in front of the substrate, seen in the viewing direction.

Patent claims

- 5 1. Electrochromic glass component, particularly for
 motor vehicle mirrors, having a layer system
 arranged on a glass substrate containing at
 least one electrochromic layer, at least two
10 electrodes, at least one ion-conducting layer,
 at least one ion-delivering layer and at least
 one ion-storing layer, wherein the two last-men-
 tioned layers may also form a layer at the same
 time, characterised in that the ion-conduction
15 layer contains a doped ion-conducting basic
 polymer.
2. Electrochromic glass component according to
 claim 1,
 characterised in that the doped ion-conducting
20 polymer is selected from polybenzimidazoles,
 (PBI), polypyridines, polyimidazoles,
 polybenzthiazoles, polybenzoxazoles,
 polyquinolines, polythiazoles, polyoxadiazoles
 and polytetrapyrenes.
- 25 3. Electrochromic glass components according to
 claim 1 or 2,
 characterised in that the doped ion-conducting
 polymer is a polymer membrane.
- 30 4. Electrochromic glass component according to
 claim 3,
 characterised in that the polymer membrane con-
 sists of a polybenzimidazole polymer.
- 35

5. Electrochromic glass component according to at least one of claims 1 to 4, characterised in that the ion-conducting layer is doped with acid.
5
6. Electrochromic glass component according to claim 5, characterised in that the layer has been doped with phosphoric acid.
10
7. Electrochromic glass component according to at least one of claims 1 to 5, characterised in that the pKa value of the free acid is ≤ 4.5 at 25 °C for the first dissociation stage.
15
8. Electrochromic glass component according to at least one of claims 1 to 7, characterised in that the ion-conducting layer has a layer thickness of 1 μm to 1 mm.
20
9. Electrochromic glass component according to at least one of claims 1 to 8, characterised in that the ion-conducting layer is applied to the substrate or a different layer of the layer system or is produced thereon.
25
10. Electrochromic glass component according to at least one of claims 1 to 9, characterised in that the ion-conducting layer is applied or produced by screen printing, immersion, blade coating, spraying or as a gel, or by a combination thereof.
30

- 5 11. Electrochromic glass component according to at least one of claims 1 to 10, characterised in that the electrochromic layer is an oxidation-reduction layer consisting of metal oxides.
- 10 12. Electrochromic glass component according to claim 11, characterised in that the electrochromic layer is a WO_3 layer having a layer thickness of 100 nm to 3,000 nm.
- 15 13. Electrochromic glass component according to at least one of claims 1 to 12, characterised in that at least one electrode is designed in the form of metallic layers having a layer thickness of 100 nm to 10 μm .
- 20 14. Electrochromic glass component according to claim 13, characterised in that a metallic electrode layer forms a reflector which may accept and conduct protons at the same time.
- 25 15. Electrochromic glass component according to at least one of claims 1 to 14, characterised in that the ion-delivering and ion-storing layer is present in the form of a composite.
- 30 16. Electrochromic glass component according to claim 15, characterised in that the composite consists of a substrate, for example of glass, metal or plastic, for example a polyester film, to which
- 35

a proton-storing layer, for example a metal oxide layer, is applied.

- 5 17. Electrochromic glass component according to claim 16,
characterised in that the composite additionally has an electrode layer in the form of metallisation.
- 10 18. Electrochromic glass component according to at least one of claims 1 to 17, characterised in that an electrochromic layer, metallisation as a reflector, a
15 proton-conducting membrane and a composite of a proton-storing layer, metallisation and a film arranged thereon, in particular of polyester, is applied to a glass substrate one after another, seen in the viewing direction.
- 20 19. Electrochromic glass component according to claim 18,
characterised in that the layer system is sealed at the end-faces,
- 25 20. Electrochromic glass component according to claim 18 or 19,
20 characterised in that the final^{layer} opposite the glass substrate is provided with a protective layer.
- 30 21. Electrochromic glass component according to one of claims 19 or 20,
characterised in that a reflection-reducing thin glass having a layer thickness of 0.3 to 3 mm is
35 used as the glass substrate.

22. Electrochromic glass component according to one of claims 19 to 21, characterised in that a conductive layer for heating the mirror is applied in front of the substrate, seen in the viewing direction.




Fig. 1

FIG. 2a





FIG. 2b



INTERNATIONAL SEARCH REPORT

International Application No.
PCT/EP 99/08572

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 G02F1/15

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 G02F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	DE 30 08 768 A (JENAER GLASWERK SCHOTT & GEN) 17 September 1981 (1981-09-17) cited in the application page 10, line 23 - line 33 page 13, line 4 - line 23 ---	1,3,5, 7-22
Y	EP 0 483 893 A (GEN MOTORS CORP) 6 May 1992 (1992-05-06) column 1, line 1 - line 10 column 2, line 53 - line 57 column 6, line 6 - line 38 ---	1,3,5, 7-22
A	EP 0 450 581 A (SONY CORP) 9 October 1991 (1991-10-09) column 3, line 14 - line 20 column 4, line 23 - line 29 column 12, line 12 - line 20 --- -/--	2

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 February 2000

Date of mailing of the international search report

29/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Petitpierre, 0

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/EP 99/08572

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98 42037 A (MOTOROLA INC) 24 September 1998 (1998-09-24) page 2, line 7 - line 11 page 8, line 19 - line 24 -----	2
A	US 5 536 808 A (CURTIS M DAVID ET AL) 16 July 1996 (1996-07-16) column 1, line 15 - line 19 column 1, line 65 - column 2, line 3 column 3, line 21 - line 25 -----	2

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/08572

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 3008768	A	17-09-1981	EP 0035766 A	16-09-1981
			JP 1639459 C	18-02-1992
			JP 3005565 B	25-01-1991
			JP 56133719 A	20-10-1981
			US 4465339 A	14-08-1984
EP 0483893	A	06-05-1992	US 5071233 A	10-12-1991
			AU 632244 B	17-12-1992
			AU 8559991 A	30-04-1992
			JP 4289826 A	14-10-1992
EP 0450581	A	09-10-1991	JP 3289067 A	19-12-1991
			JP 3287623 A	18-12-1991
			DE 69110724 D	03-08-1995
			DE 69110724 T	07-03-1996
WO 9842037	A	24-09-1998	NONE	
US 5536808	A	16-07-1996	NONE	